



FARAGAM PETRO TECH

Design , Materials Supply & Implementing Projects of Oil ,Gas & Petrochemical

Date:

No:

Att:

FARAGAM PETRO TECH FARAGAM PETRO TECH FARAGAM PETRO TECH

Bitumen SC 30 Analysis

Slow Curing SC-30 Bitumen Cutback			
Property	Min	Max	Test Method
KINEMATIC VISCOSITY AT 60°C mm ² /s	30	60	ASTM D2170
FLASH POINT (TAG OPEN-CUP),°C	60	-	ASTM D3143
DISTILLATE TEST: DISTILLATE, VOLUME PERCENT OF TOTAL DISTILLATE AT 360°C:			
TOTAL DISTILLATION UP TO 360°C, VOLUME%	10	45	ASTM D402
SOLUBILITY IN TRICHLOROETHYLENE,%	99	-	ASTM D2042
VISCOSITY AT 60°C	250	5000	ASTM D2171
TEST ON RESIDUE FROM DISTILLATION:			
PENETRATION AT 100%	50	-	ASTM D5
DUCTILITY AT 25°C	100	-	ASTM D113



#3,First Floor, Aein Building, West Hasht Behesht, Isfahan, Iran
Tel/Fax: +98-3132684505
Postal code: 8154794916

www.faragam-co.com

E-mail:info@faragam-co.com